This bonding agent is one step for priming and bonding

Meta P&Bond adhesive system is wet bond adhesive system that is activated by visible light curing. This bonding agent is one step for priming and bonding

INDICATIONS

- Bonding for direct composite restoration
- Bonding for Porcelain, composite, metal repair, set amalgam, post
- Bonding for porcelain veneer
- Bonding for amalgam and indirect bonding procedures with Metacem adhesive resin cement

INSTRUCTIONS

- (1) Isolation: Rubber dam is the preferred method for isolation.
- Cavity preparation: prepare cavity with minimal tooth reduction.
 Tooth conditioning /Dentin pretreatment: Apply 37% Meta Etchant gel to available
- enamel/dentin for 15 seconds.

 (4) Rinse and Blot dry: Remove gel with aspirator tube and rinse for 20 seconds. Blot dry conditioned area with a moist cotton pellet, Blot dry to keep moist, do not rub.
- (5) Bonding: Apply a double coat of Meta P&Bond by using mircrobrush. Gently air dry for 5 seconds, Light cure for 10 seconds.
- 6 Restoration or cementation.

— CONTRAINDICATION

Meta P&Bond should not be used if patients are known to be allergic to and of the ingredients

SIDE EFFECTS

None known to date

CAUTIONS

- Avoid contact of Meta P&Bond with the skin / mucous membrane, or eyes.
- Unpolymerized Meta P&Bond may cause slightly, reversible irritation or lead to a general sensitisation againsts methacrylates.
- Keep away from child.
- For dental use only.
- Do not use Meta P&Bond after the date of

STORAGE

- Close bottle immediately after use to minimize evaporation
- Exposure to light may be lead to premature polymerization
- Store at 18°C~24°C(64°F~75°F)

COMPONENT

- Meta P&Bond 5ml/q in bottle
- Microbrush
- Instruction for use

SHFLELIFE

2 years from the manufactured date.

SYMBOLS



Use By

LOT Batch Code

CE-Mark and identification number of notified body. Product conforms to the essential requirements of the Medical Device Directive 93/42/EEC



Attention. See instruction for use

Manufacturer

Made in Korea

META BIOMED COLTD

Manufactured by

META BIOMED CO.LTD.

634, Yeonje-ri, Gang-oe-myeon, Cheong-won-gun Chungcheongbuk-do, Korea Tel:+82-43-216-0433 Fax:+82-43-217-1988 E-mail: info@meta-biomed.com Web site: http://www.meta-biomed.com

